

CUGLATON® SK-B

- CUGLATON SK-B is a shrink-proof cement mortar based on Portland cement, specially developed for prefab construction.
- CUGLATON SK-B has excellent flow properties and a high stability, with a low water dry cement factor of maximum 0.28, which is ideal for pumping.

Applications

Civil and public utilities / prefab construction	Grouting prefab concrete elements Casting gains
Industrial construction	Filling in tank bottoms Filling steel section for fire resistance
Concrete construction and hydraulic engineering	Casting curb profiles

Classification in accordance with CUR Recommendation 24

Non-shrink mortars

Mortar sort	Grout
Mortar type	0,5 mm
Strength class	K 50
Environment class	X0 t/m XA3
Swelling	> 0,1% < 2,0 %
Average shrinkage	< 0,96 mm/m



Directions for use

Pre-treatment

The surface onto which CUGLATON SK-B has to be applied needs to be clean. The cement skin coating should be removed and no free water may be present.

- Pre-treatment with water.
The surface must only be moistened with water (Please note: No free water!)
- or
- Pre-treatment CUGLACRETE HECHTPRIMER CEMENTGEBONDEN or CUGLACRETE HECHTPRIMER EPOXY SEALER. For an optimum bond we advise the use of CUGLACRETE HECHTPRIMER CEMENTGEBONDEN, a cement polymer modified system, or CUGLACRETE HECHTPRIMER EPOXY SEALER, an epoxy-based system.

Mixing

Mechanically mix CUGLATON SK-B until it becomes a homogeneous mixture. Mixing time depends on the type of mixer, approx. 3 minutes.

Water range

Water range: 5,2 – 5,6 ltr/20 kg mortar. Dose, within the indicated water range, with plenty of water so as to produce a mortar with a flow of approx. 650 mm.

Follow-up treatment

The finished surface must be carefully protected against dehydration with CUGLA CURING COMPOUND, or by covering with a plastic sheet.

Storage and shelf life

If stored in a dry place it has a shelf life of up to 6 months after production date, as stated on the packaging.

Technical data at 20°C/65% RH

Maximum grain size		0,5	mm
Cement type		Portland	
Water range		5,2 - 5,6	ltr/20 kg mortar
Consumption per m³ approx.		1620	kg
Voluminous mass		2050	kg/m ³
Layer thickness		30	mm max.
Flow measure	t = 0 min.	650	mm
("flow gutter" method)	T = 60 min.	400	mm
Initial setting time		30	minutes
Swelling v/v ASTM C827		> 0,1 en < 2,0	%
Drying shrinkage NEN 3534	24 hours	< 0,3	mm/m
	28 days	< 1,9	mm/m
Fire classification (NEN-EN 13501-1)		A1	

Strength development ISO 679		24 hours	2 days	3 days	7 days	28 days	91 days
Tensile strength	N/mm ²	5	7	8	9	10	
Compressive strength	N/mm ²	27	43	51	65	75	84
Compressive strength (150x150x150 mm)	N/mm ²					81	

Health aspects

Cugla advises:

- To wear the correct gloves and goggles.
- To avoid contact with eyes and skin.
- In case of contact with the eyes, to rinse immediately with plenty of water and seek medical advice.
- In case of swallowing the product immediately contact a doctor and show the package or the safety data sheet.

For detailed information we refer to the safety data sheet, SDS Cuglaton SK-B, on our website.

Changes to this document will not automatically be issued. Any previous product information hereby becomes null and void. The above data is provided to the best of our knowledge. The tests have been carried out under laboratory conditions. We will not accept any liability for the results achieved on the work, now that we have no influence on the process nor the specific conditions of the work.

Our general sales, delivery and payment conditions apply to all our transactions and are available at www.cugla.com.