

## CUGLA® LR CON. 20%\* SPL

Admixture in accordance with NEN-EN 934-2



0956-CPR-1501

CUGLA LR is the result of the development of a new generation of super plasticizer based on polycarboxylates.

CUGLA LR gives concrete mortar a unique combination of properties, namely:

- Very high workability for 90 minutes
- Higher initial and final strengths due to the prevention of micro-bleeding
- Optimal density

This makes CUGLA LR ideal for the following applications:

- High Strength Concrete and a long workability
- Watertight concrete constructions
- Concrete mortar suitable for a long transport time

Depending on wishes, requirements and circumstances, an CUGLA LR type is available or can be developed.

### Advantages

<b>Workability</b>	The strong plasticizing effect can give concrete mortar with a very low water-cement factor a plastic and long workability. With a modified mixture composition it is possible to produce a highly stable self-compacting concrete mortar.
<b>Strength</b>	High initial and final strength.
<b>Durability</b>	Watertight concrete, environment class XA3.
<b>Cement savings</b>	Standard compositions can be produced with considerably less cement.
<b>Compaction</b>	<b>Production of self-compacting concrete mortar is possible without the segregation of the concrete mortar.</b>

### Product properties

<b>Product name</b>	CUGLA LR SPL			
<b>Category</b>	Superplasticizing admixture			
<b>Manufacturer/supplier</b>	CUGLA			
<b>Colour code</b>	Grey			
<b>Effective component</b>	Polycarboxylate ether			
<b>Physical state</b>	Liquid			
<b>Colour</b>	Brown			
<b>Soluble in water</b>	Yes			
<b>Concentration</b>	%	20		
<b>pH</b>		2 - 8		
<b>Absolute density</b>	kg/l	1,05 ± 0,02		
<b>Dry material content</b>	%	20 ± 1,0		
<b>Total chlorine</b>	%	< 0,1		
<b>Water soluble chlorine</b>	%	< 0,1		
<b>Alkali content</b>	%	1,0		

### Use and dosage instructions

<b>Manner / moment of dosage</b>	Preferably add to the last part of the mixing water				
<b>Recommended dosage</b>	Depending on the desired consistency of the concrete				
<b>Processing temperature</b>	5 - 30 °C				
<b>Shelf life and storage</b>	Up to 1 year after manufacturing date, frost-free				
<b>Suitable for use in</b>	Non-reinforced concrete Reinforced concrete Pre-stressed concrete				
<b>Not compatible with</b>	Aluminium cement: only in consultation with CUGLA Other admixtures: only in consultation with CUGLA				
<b>Concentration</b>	<b>%</b>	20			
<b>Maximum recommended dosage</b>	<b>% in regard to cement</b>	2,6			
	<b>cc per 100 kg cement</b>	2475			
	For dosing higher than the maximum recommended dosage, please contact the Product Manager of Cugla for advice				

### Packaging

In cans, barrels, containers and/or bulk

### Health and environmental factors

Cugla recommends that when using Cugla admixtures:

- Should the product come in contact with eyes, rinse immediately with water and seek medical advice.
- Should the product come in contact with skin, wash immediately with soap and water.
- Should you feel ill, consult a doctor, showing him/her this sheet or the safety information sheet.

**For detailed information we refer to the safety data sheet, SDS Cugla LR con.20% SPL, on our website.**

Changes to this document will not automatically be issued. Any previous product information hereby becomes null and void. The above data is provided to the best of our knowledge. The tests have been carried out under laboratory conditions. We will not accept any liability for the results achieved on the work, now that we have no influence on the process nor the specific conditions of the work.

Our general sales, delivery and payment conditions apply to all our transactions and are available at [www.cugla.com](http://www.cugla.com).