

CUGLATON® HOOGOVEN GIETMORTEL 4 MM

- CUGLATON HOOGOVEN GIETMORTEL 4 mm is a shrink-proof, low viscous mortar that fills all cavities and spaces based on blast-furnace cement.
- CUGLATON HOOGOVEN GIETMORTEL 4 mm meets the sustainability requirement conform CUR Recommendation 89 'Measures to prevent damage to concrete by alkali-silica reaction (ASR)'.

Classification in accordance with CUR Recommendation 24


Non-Shrink mortar

Mortar sort		Grout
Mortar type		4 mm
Strength class	7 days	K 50
Exposure class		X0 t/m XA3
Swelling		> 0,1% < 2,0 %
Shrinkage		< 0,75 mm/m



Cuglaton Hoogoven Gietmortel 4 mm is suitable for repair methods in accordance to NEN-EN 1504-3 table 1

- 4.4 Structural strengthening by adding mortar or concrete
- 7.1 Increasing cover to reinforcement with mortar or concrete
- 7.2 Replacing of contaminated or carbonated concrete

 0956	
CUGLA BV Rudonk 6a 4824 AJ BREDA 20 0956-CPR-0707	
NEN-EN 1504-3	
DoP: EM0051-02-10-2023	
Concrete repair mortar based on cement for structural application	
Compressive strength	Class R4
Chloride ion content	≤ 0,05 %
Adhesive bond	≥ 2,0 MPa
Carbonation resistance	NPD
Elastic modulus	≥ 20 GPa
Thermal compatibility (freeze and thaw, 50 cycli with salt)	≥ 2,0 MPa
Capillary absorption	≤ 0,5 kg/(m ² *h ^{0,5})
Dangerous substances	Comply with 5.4
Reaction to fire	NPD

Directions for use

Pre-treatment

The surface onto which CUGLATON HOOGOVEN GIETMORTEL 4 mm has to be applied needs to be clean.

The cement skin coating should be removed and no free water may be present.

- Pre-treatment with water.
The surface must only be moistened with water (Please note: No free water!)
- or
- Pre-treatment CUGLACRETE HECHTPRIMER CEMENTGEBONDEN or CUGLACRETE HECHTPRIMER EPOXY SEALER.
For an optimum bond we advise the use of CUGLACRETE HECHTPRIMER CEMENTGEBONDEN, a cement polymer modified system, or CUGLACRETE HECHTPRIMER EPOXY SEALER, an epoxy-based system.

Mixing

Mechanically mix CUGLATON HOOGOVEN GIETMORTEL41 mm until it becomes a homogeneous mixture.

Mixing time depends on the type of mixer, approx. 3 minutes.

Water dosage

Water bandwidth: 2,2 – 2,6 ltr/20 kg mortar. Dose, within the indicated water bandwidth, with plenty of water so as to produce a mortar with a flow of approx. 450 mm.

Follow-up treatment

The finished surface must be carefully protected against dehydration with CUGLA CURING COMPOUND, or by covering with a plastic sheet.

Storage and shelf life

If stored in a dry place it has a shelf life of up to 6 months after production date, as stated on the packaging.

Health aspects

Cugla advises:

- To wear appropriate personal protective equipment (PPE).
- To avoid contact with eyes and skin.
- In case of contact with the eyes, to rinse immediately with plenty of water and seek medical advice.
- In case of swallowing the product immediately contact a doctor and show the package or the safety data sheet.

Safety data sheets, SDS, are available via our website www.cugla.com.

Cuglaton® does not contain any chlorine, nor any other corrosive substances. For application at temperatures < 0 °C please contact Cugla B.V.

EC declaration of conformity

The undersigned declares that this concrete repair product, as mentioned in this technical data sheet, meets the requirements according to NEN-EN 1504-3.

The Factory Production Control (FPC) is evaluated by KIWA NEDERLAND BV – RIJSWIJK The Netherlands. The EC certificate of conformity, number 0956-CPR-0707, is awarded by KIWA NEDERLAND BV Certification on 01-07-2013.

Breda, 02 Octobre 2023

I. Velthoen
Technical Director

Technical data at 20°C/65% RH

Property	Standard	Value	
Maximum grain	NEN-EN 12192-1	4,0	mm
Ground granulated blast furnace slag		> 50	%
Water bandwidth		2,2 - 2,6	ltr/20 kg
Exposure class	NEN-EN 206-1	X0 t/m XA3	
Layer thickness		120	mm max.
Density	NEN-EN 12350-6	2250	kg/m ³
Viscosity - Flowcone	EN 13395-2	t = 0 > 450 min	mm
Setting time	ASTM C827/87	20	minutes
Air content	NEN-EN 12350-7	3,0	%
Compressive strength	NEN-EN 12190		
		1 day 30	N/mm ²
		7 days 60	N/mm ²
		28 days 90	N/mm ²
Adhesive strength		28 days 3,8	N/mm ²
after freeze and thaw (50 cycles with salt)	NEN-EN 12687-1	2,8	N/mm ²
Elastic modulus	NEN-EN 13412	38900	N/mm ²
Carbonation resistance		NPD	
Capillary absorption	NEN-EN 13057	0,12	kg/(m ² *h ^{0,5})

Changes to this document will not automatically be issued. Any previous product information hereby becomes null and void. The above data is provided to the best of our knowledge. The tests have been carried out under laboratory conditions. We will not accept any liability for the results achieved on the work, now that we have no influence on the process nor the specific conditions of the work.

Our general sales, delivery and payment conditions apply to all our transactions and are available at www.cugla.com.