

CUGLATON® TIKSO K50

- CUGLATON TIKSO K50 is a shrink-proof cement mortar with thixotropic properties, specially developed for constructing prefabricated construction systems, without the need for shuttering.
- CUGLATON TIKSOMORTEL K50 can be very easily pumped, is stable and has excellent bonding properties.
- CUGLATON TIKSOMORTEL K50 can be applied in layers up to approx. 60 mm thick.

Applications

Civil and public utilities / prefabricated construction	Filling clearances under prefabricated concrete elements through pumping Placing prefabricated concrete elements in mortar beds Filling vertical joints between prefabricated concrete elements
Industrial construction	Horizontal bonding of anchors Filling crane gantries under slopes Undergrouting steel baseplates
Concrete construction and hydraulic engineering	Horizontal bonding of anchors Filling vertical joints between prefabricated concrete elements

Classification in accordance with CUR Recommendation 24

Non-shrink mortars

Mortar sort	Trowel mortar
Mortar type	0,5 mm
Strength class	K 50
Environment class	X0 t/m XA3
Swelling	> 0,1% < 2,0 %
Shrinkage	< 0,80 mm/m



Directions for use

Pre-treatment

The surface onto which CUGLATON TIKSOMORTEL K50 has to be applied needs to be clean.

The cement skin coating should be removed and no free water may be present.

- Pre-treatment with water.
The surface must only be moistened with water (Please note: No free water!)
- or
- Pre-treatment CUGLACRETE HECHTPRIMER CEMENTGEBONDEN or CUGLACRETE HECHTPRIMER EPOXY SEALER.
For an optimum bond we advise the use of CUGLACRETE HECHTPRIMER CEMENTGEBONDEN, a cement polymer modified system, or CUGLACRETE HECHTPRIMER EPOXY SEALER, an epoxy-based system.

Mixing

Mechanically mix CUGLATON TIKSOMORTEL K50 until it becomes a homogeneous mixture. Mixing time depends on the type of mixer, approx. 3 minutes.

Water range

Water bandwidth: 3,0 – 3,4 ltr/20 kg mortar. Dose, within the indicated water bandwidth, with plenty of water so as to produce a mortar with a flow of approx. 140 mm.

Follow-up treatment

The finished surface must be carefully protected against dehydration with CUGLA CURING COMPOUND, or by covering with a plastic sheet.

Storage and shelf life

If stored in a dry place it has a shelf life of up to 6 months after production date, as stated on the packaging.

Technical data at 20°C/65% RH

Maximum grain size			0,3	mm
Cement type			Portland	
Water range			3,0 – 3,4	ltr/20 kg mortar
Consumption per m³ approx.			1780	kg
Voluminous mass			2050	kg/m ³
Layer thickness			60	mm max.
Flow measure	EN 13395-2	t = 0 min.	140	mm
Initial setting time	ASTM C827/87		30	minutes
Swelling v/v	ASTM C827/87		> 0,1 en < 2,0	%
Shrinkage	EN 12617-4	24 hours 28 days	< 0,3 < 1,3	mm/m mm/m
Fire classification	EN 13501-1		A1	

Strength development	EN 196-1	16 hours	24 hours	7 days	28 days
Tensile strength	N/mm ²	2	4	7	9
Compressive strength	N/mm ²	32	44	65	80

Cuglaton[®] does not contain any chlorine, nor any other corrosive substances. For application at temperatures < 0 °C please contact Cugla B.V.

Health aspects

Cugla advises:

- To wear appropriate personal protective equipment (PPE).
- To avoid contact with eyes and skin.
- In case of contact with the eyes, to rinse immediately with plenty of water and seek medical advice.
- In case of swallowing the product immediately contact a doctor and show the package or the safety data sheet.

Safety data sheets, SDS, are available via our website www.cugla.com.

Changes to this document will not automatically be issued. Any previous product information hereby becomes null and void. The above data is provided to the best of our knowledge. The tests have been carried out under laboratory conditions. We will not accept any liability for the results achieved on the work, now that we have no influence on the process nor the specific conditions of the work.

Our general sales, delivery and payment conditions apply to all our transactions and are available at www.cugla.com.